

MD-Mix Water



Basis	Epoxy Putty
Color (mixed)	white
Work life	25 til 30
Curing time	8 til 12 minutes
Full Strength	24h
Working temperature	+10°C til+30°C
Curing temperature	+6°C til +30°C
Shear Strength (DIN 53283) N/mm ²	6
Mix rate	1:1
Shore Hardness D	82
temperature resistance	-50°C til +120°C
Shrinking %	ca. 0,05
Thermal Conductivity W/mK	0,50 W/m-K
Dielectric capacity kv/mm	3,0 kV/mm
Gap filling mm	15

Very easy to use and useful for emergency repairs in industries, workshops, marine, automotive, construction and also for household use.

Bergheimer Str. 15 ■ D-53909 Zülpich ■ Tel. 02252/94150 ■ info@marston-domsel.de ■ www.marston-domsel.de Revision 08/2011 Page 1 of 2

Our information sheets and other publications are intended to provide advice based on the knowledge at our disposal. However, contents are not legally binding with regards to processing and application as these do not fall within our field influence. The right is reserved to make modifications in the interests of improvement or further development of the product.



How to use:

- 1. Make the application surface clean, dry and free from dust, rust, oil etc.
- 2. If the surface to be applied is smooth, roughen with sand-paper for better adhesion.
- 3. Wear protective eye glasses and hand-gloves whenever necessary.
- 4. Cut the required quantity of putty stick.
- 5. Mix the putty homogeneously and apply the mixture immediately on the surfaces to be bonded.
- 6. Apply pressure to hold the surface until the adhesive cures.

24 pcs á 56 g 12 pcs. á 115 g

Art.Nr. MIX.W.56 Art.Nr. MIX.W.115 **Technical** Data Shee

Bergheimer Str. 15 ■ D-53909 Zülpich ■ Tel. 02252/94150 ■ info@marston-domsel.de ■ www.marston-domsel.de Revision 08/2011 Page 2 of 2

Our information sheets and other publications are intended to provide advice based on the knowledge at our disposal. However, contents are not legally binding with regards to processing and application as these do not fall within our field influence. The right is reserved to make modifications in the interests of improvement or further development of the product.