

ELASTOSIL® M 4440

RTV-2 Silicone Rubber / Mold Making

Characteristics

Pourable, condensation-curing, two-component silicone rubber that vulcanizes at room temperature and features

Special characteristics

- Very good flowability and self-deaeration
- Medium Shore A hardness (approx. 37)
- Very good resistance to common casting resins

Application

ELASTOSIL® M 4440 is a general-purpose mold-making material suitable for casting resins, wax, gypsum, etc.

ELASTOSIL® M 4440 is preferred when no or only minor undercuts are involved and a certain inherent stability of the mold is required.

Processing

ELASTOSIL® M 4440 is cured by adding Catalyst T 37 for long pot lives and curing times, and Catalysts T 40 or T for short pot lives and curing times.

The pot life figures indicate the time at 23 °C / 50 % rel. humidity required for the catalyzed mix to attain a viscosity of 100 000 mPa s and still be just pourable.

Catalyst	Pot life, approx. [min]	Curing time (tack-free), approx. [h]
3 % T 37	80	8-10
2 % T 40	50	6-7
2 % T	40	4-5
4 % T	15	1-2

Comprehensive instructions are given in our leaflet "WACKER RTV-2 Silicone Rubber - Processing."

Product data (uncured)

Property	Test method	Unit	Value
Color			White
Density at 23 °C		[g/cm ³]	1.25
Viscosity at 23 °C, after stirring	ISO 3219	[mPa s]	20,000

These figures are intended as a guide and should not be used in preparing specifications.

Product data (catalyzed with 3 wt % Catalyst T 37)

Property	Test method	Unit	Value
Viscosity at 23 °C	ISO 3219	[mPa s]	15,000

These figures are intended as a guide and should not be used in preparing specifications.

Product data (cured)

Property	Test method	Unit	Value
Density at 23 °C in Water	ISO 2781	[g/cm ³]	1.23
Hardness Shore A	ISO 868		37
Tensile strength	ISO 867	[N/mm ²]	2.5
Elongation at break	ISO 867	[%]	220
Tear strength	ASTM D 624 B	[N/mm]	4.5
Linear shrinkage		[%]	0.4

Cured, with 3 wt % of Catalyst T 37, after 4 days at 23 °C / 50 % rel. humidity.

These figures are intended as a guide and should not be used in preparing specifications.

Detailed information on other mold-making compounds in the ELASTOSIL® M range is contained in our brochure "ELASTOSIL® M. Mold-Making Compounds For Maximum Precision".

Storage

ELASTOSIL® M 4440 has a shelf life of at least 12 months when stored between 5 °C and 30 °C in the tightly closed original container. The 'Best use before end' date of each batch appears on the product label.

Catalysts T 37 and T 40 have shelf lives of at least 12 months if stored in the sealed original bottles between 5 °C and 25 °C. Catalyst T has a maximum shelf life of 9 months under the same conditions.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety information

Being a condensation-curing silicone rubber, ELASTOSIL® M 4440 contains only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Catalysts T, T 37 and T 40 contain a tetraorganotin compound, are flammable (flash points 38 °C, 53 °C and 34 °C respectively) and may cause irritation in contact with the eyes and skin. Adequate protective measures are required.

Detailed safety information is contained in each Material Safety Data Sheet, which can be obtained from our sales offices.

Additional information

Please contact your nearest WACKER subsidiary.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001. The Business Unit Elastomers of the Division Silicones is ISO/TS 16949 certified.

WACKER

and ELASTOSIL® are registered trademarks of Wacker-Chemie GmbH.

Version 3.00 from 29-01-04 replaces Version 2.00 from 22-08-03

For technical, quality, or product safety questions, please contact:

Wacker-Chemie GmbH
WACKER-SILICONES
Hanns-Seidel-Platz 4
D-81737 Munich, Germany

Silicone-Info Service
Germany:
Tel.: 0-800-6279-800
International:
Phone: +800-6279-8000

www.wacker.com
silicones@wacker.com