

# Repair Stick Aqua

## Introduction

The uncomplicated solution for all repair and maintenance work.

Easy to use:

Cut off - knead - use

Always the right portion, even for small repairs.



Ideal for quick repairs on damp and wet surfaces and for underwater applications. Patches and seals cracks, holes, leakages and surface damages on:

- fuel and water tanks
  - radiators
  - electrical switchboards
  - sanitary installations
  - swimming pools
- and in the marine sector.

## Technical data

Composition	Epoxy resin and ceramic fillers
Pot life at 25 g material and at +20°C	15 Min.
Density of the mixture	1,9 g/cm <sup>3</sup>
Processing temperature	+10 to +40 °C
Curing temperature	+6 to +40 °C
Colour after curing	white
Gap covering power to maximum	15 mm
Handling strength (35% strength/+20°C) after	30 Min.
Capable of bearing mechanical loads(50% strength/+2	1 h
Final strength (100%) at +20°C after	24 h
Pressure (DIN 53281-83)	75 N/mm <sup>2</sup>
Shore hardness D	65
ac. to DIN 53283	6,2 (Steel sandblasted) N/mm <sup>2</sup>
Temperature resistance	50 bis +120 (kurzfr. +150) °C

## Pretreatment of the surface

To ensure a perfect bond, the surfaces to be joined must be clean and dry (e.g., clean and degrease using Cleaner S or Plastic Cleaner). Smooth surfaces should be roughened, e.g. by sandblasting.

## Processing

WEICON Repair-Sticks cover gaps of max. 15 mm per procedure. The pot life given is for a material quantity of 25 g at room temperature. If larger quantities are used, the curing time will be faster due to the typical reaction heat of epoxy resins (exothermic reaction).

Similarly, higher ambient temperatures shorten the cure time (as a rule of thumb, every +10°C increase above room temperature will halve working and curing time). Temperatures below +16°C will extend working and curing times considerably, while below about +5°C, no reaction will take place at all.

Physiological properties / health and safety at work

WEICON Repair Sticks, when properly handled and completely cured, are toxicologically essentially harmless. When using these adhesives, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.de](http://www.weicon.de)) must be observed.

## Storage

When kept at a constant room temperature of about +20°C and unopened in dry conditions, WEICON Repair Sticks will keep for at least 18 months.

Avoid direct sunlight.

## Note

Any product specifications and recommendations given herein must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do warrant the continuously high quality of our products being free from defects in accordance with and subject to our General Sales Conditions. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

### WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster  
P.O. Box 84 60 · DE-48045 Münster  
Germany

Tel. +49 (0) 251 / 93 22-0  
Fax +49 (0) 251 / 93 22-244  
Fax +49 (0) 251 / 93 22-233 Export  
[www.weicon.de](http://www.weicon.de) · [info@weicon.de](mailto:info@weicon.de)

### WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216  
Dubai · U.A.E

Phone +971 4 880 25 05  
Fax +971 4 880 25 09  
Mobile +971 50 545 99 83  
[www.weicon.ae](http://www.weicon.ae) · [info@weicon.ae](mailto:info@weicon.ae)

### WEICON Inc.

20 Steckle Place · Unit 20  
Kitchener · Ontario · N2E 2C3  
Canada

Phone +1 519 896 5252  
Fax +1 519 896 5254  
Cell +1 519 590 5168  
[www.weicon.ca](http://www.weicon.ca) · [info@weicon.ca](mailto:info@weicon.ca)

### WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi  
Arifağa Sokak No: 29 Kat: 3  
34530 Yenibosna – İstanbul Turkey  
[www.weicon.biz.tr](http://www.weicon.biz.tr) · [info@weicon.biz.tr](mailto:info@weicon.biz.tr)

### WEICON Romania SRL

Str. Depozitelor 22  
540240 Targu Mures, jud. Mures Romania  
[www.weicon.com](http://www.weicon.com) · [office@weicon.com](mailto:office@weicon.com)